

Information

Collection name: Sable
Design name: Sable
Tariff item number: 52093900
Launch date: 9-2010

Number of colourways : 34

Vertical repeat (V): plain
Horizontal repeat (H): plain
Roll diameter (50 meters): 19.0 cm 7 3/8 "
Average piece length: 50 m
Double folded face in: Yes No
Face out: Yes No
Face in: Yes No
Minimum for special colour: 1000 m
Delivery time special lab dip/sample: weeks



Fabric type

Total composition: 100% Cotton

Yarn warp 1

Yarn composition warp: 100% Cotton Not high tenacity

Natural Staple Man made Filament

Specify: Combed Carded Napped Not napped
 Textured Not textured Cabled Folded

Yarn sizes warp: 2/16's

Threads per cm warp: 25.2 Turns per meter (TPM): NA

Yarn weft 1

Yarn composition weft: 100% Cotton Not high tenacity

Natural Staple Man made Filament

Specify: Combed Carded Napped Not napped
 Textured Not textured Cabled Folded

Yarn sizes weft: 2/16 cotton slub

Threads per cm weft: 11.02 Turns per meter (TPM): NA

Average yarn number

11.52 (100 x number of single threads per cm² divided by g/m²)

Width selvedge to selvedge

Full width: 142 cm 55 7/8 "

Useable width: 140 cm 55 1/8 "

Weight: 316 g/m²

Construction: 25.2x11.02 Woven Non woven Hand woven

Plain weave Twill Satin Dobby
 Jacquard Pile Other:

Category

- Printed Piece dyed Yarn dyed Scoured
 Other:
-

Type of print/dye

- Disperse Reactive Vat Pigment

Type of finish






- Calender Sanforized Thermofixed Washed
 Other: Stenter None

After treatment

- Soil and stain repellent Specify:
 Waterrepellant Specify:
 Flame retardant Specify:
 Brushed/emersed
 Bio treatment Specify:
 Other Specify:
 None

Care codes

- Washable: Wash 30°C gentle cycle
 Iron: Hot iron at max 200°C
 Tumble dry: Do not tumble dry
 Bleach: Do not bleach
 Dry clean P: Dry-cleaning in perchloroethylene gentle cycle
 Comments:

Care symbols:     

Use codes

- Curtains/draperies: Yes No
 IMO – Marine: Yes No
 Upholstery: Yes No
 Light upholstery: Yes No
 Bed covering: Yes No
 Accessories: Yes No
 Comments:

FR Standards

CAL 117 (Complies)	Yes	Comments:
FMVSS 302 (Pass)	No	Comments:
NFPA 260/UFAC (Class I)	Yes	Comments:
BS5852 Source 0 (Pass)	Yes	Comments:

Specification

Weight:	EN 12127	316 g/m ²
Total composition:	ISO 1833	100% Cotton
Wear resistance:	ISO 12947-2	25,000 rubs
Colour fastness to wear:	ISO 12947-2	3-4
Pilling:	ISO 12945-2	4

Colour fastness dry rub:	ISO 105-X12	4
Colour fastness wet rub:	ISO 105-X12	3-4
Colour fastness to light:	ISO 105-B02	5
Colour fastness to water:	ISO 105-E01	4-5
Tearing strength warp:	ISO 13937-1	120 N
Tearing strength weft:	ISO 13937-1	130 N
Tensile strength warp:	ISO 13934-1	1100 N/5cm
Tensile strength weft:	ISO 13934-1	470 N/5cm
Elongation warp:	ISO 13934-1	24.5 %
Elongation weft:	ISO 13934-1	15.5 %
Seam slippage warp:	ISO 13936-2	4 mm
Seam slippage weft:	ISO 13936-2	8 mm

Resistance to domestic washing 30°C (ISO 6330)

Dimensional change warp: +2.52 %	After ironing: +2.25 %
Dimensional change weft: -1.33 %	After ironing: -1.26 %
Colour fastness: 3-4	ISO 105 C06

Resistance to domestic washing 60°C (ISO 6330)

Dimensional change warp: +1.56 %	After ironing: +1.33 %
Dimensional change weft: -1.82 %	After ironing: -1.52 %
Colour fastness: 3-4	ISO 105 C06

Resistance to dry cleaning P (ISO 105 D01)

Dimensional change warp: +0.53 %	After ironing: +0.53 %
Dimensional change weft: +0.07 %	After ironing: +0.13 %
Colour fastness: 4-5	ISO 105 D01

Dimensional stability (ISO 3759)

Dimensional change warp: +0.33 %

After ironing with steam: +1.26 %

After ironing without steam: 0 %

Dimensional change weft: 0 %

After ironing with steam: +0.47 %

After ironing without steam: 0 %

Wyzenbeek test (ASTM D 4157) Method using #10 cotton duck

General contract upholstery
5,000 Double rubs

Heavy upholstery duty

Unrated

Wyzenbeek test (ASTM D 4157) Method using wire screen method

Light duty
12,000 Double rubs

Medium duty

Heavy duty

Unrated